



**LAMPIRAN-LAMPIRAN**

**Lampiran 01. Dokumentasi penelitian uji *impact***




Gambar 1. Perendaman buah lontar hari pertama dan dua minggu



Gambar 2. Proses pengeringan serat dan bentuk patahan

Lampiran 02. Tabel hasil uji *impact* dan grafik kekuatan *impact*

No. Spesimen	Fraksi Volume Komposit Serat Lontar – Epoxy		
	30%	40%	50%
	Kekuatan Impak (J/mm <sup>2</sup> )		
1	2,032	3,000	3,975
2	2,000	3,000	3,890
3	1,950	2,925	4,128
4	1,978	3,028	4,120
5	2,000	2,872	3,860
<b>Rata-rata</b>	<b>1,992</b>	<b>2,965</b>	<b>3,995</b>



## Grafik Regresi Impact-Fraksi Volume

